PRODUCT DESCRIPTION


Moland engineered wood flooring



Date: Jan. 2021

| Item number: | 14301251 |
|---------------|------------------------|
| Product name: | Moland Loc Parket, Ash |

Picture



Picture no. 1

Picture no. 2

Product description

| Appearance | Parquet with natural yellowish to slight brown color (or ash wood in white color finishing), with brown and dark brown strips and clearly marked structure and characteristic for ash dark heartwood and knots. The ash floor characterizes with large changeability of tints. |
|------------------------------|--|
| Classification ac. To N13489 | Free Class, Living |
| Pattern of surface | 3 strips |
| Finishing | 7 layers, 2 layers of UV filler + 5 layers of UV lacquer |
| Lacquer | Uv lacquer, Matt, gloss 9-12 |
| Oil | - |
| Hardness | Hard wood |
| Floor heating installation | 27° on top off wood floor |

Dimensions

| Length | 2190 mm |
|-----------|---------|
| Width | 182 mm |
| Thickness | 13,3 mm |
| Top layer | 2,7 mm |

| \boxtimes | Cleaning and maintenance instructions - www.moland.dk | |
|-------------|---|--|
| | Can be used for eco-label construction. | |
| | FDV-documentation – www.moland.dk | |
| | | |

Lamel sizes

- Up to 1,5% of the material in delivery can be shorter for 30 mm.
- Above 80% lamellas with length of 150-250 mm is acceptable (not applicable to the lamellas at the ends of boards the minimum length 50 mm).

PRODUCT DESCRIPTION Moland engineered wood flooring

moland"//

Date: Jan. 2021

Technical specification

| Dimension | 13,3x182x2190 mm | Delamination | Not allowed |
|----------------------------|----------------------|--------------------------------------|-----------------------------------|
| Top layer | 2,7 mm | Torn grain | Not allowed |
| Middle layer | 8,4 mm | Colour on bevel and surface | Homogeneous expression |
| Bottom layer | 2 mm | Pressure marks | Not allowed |
| Locking method end | M5 | Product marking | CE |
| Locking method longside | М5 | Boards per packet/ m ² | 9 boards =3,58 m ² |
| Fire class | D _{fl} - s1 | Packet per pallet/ m ² | 40 packets =143,49 m ² |
| Formaldehyde content | E1 | | |
| Thermal conductivity | 0,11 W/mk | | |

Production tolerance

| Moisture content | 7% + -2% |
|---------------------------|---|
| Height difference | \leq 0,2 mm, 0,3 mm to a limited extent |
| Width | ± 0,2 mm |
| Length | ± 0,1% |
| Squareness | ± 0,2% over the width |
| Crosswise bending | ± 0,2% over the width |
| Longitudinal bending | ± 1% of the length |
| Spring across the element | \leq 0,1% over the length |

Grading

| Fresh knots | Healty, integrated not limited | |
|-----------------------|---|--|
| Cracked filled knots | Black unsound (fillet with dark brown putty) | |
| Dead knots | \leq 20 mm diameter / filled with dark brown putty. | |
| Dark lines | Allowed - moderately | |
| Cracks | Not allowed | |
| Bark pockets | Without limitations | |
| Sapwood | Allowed | |
| Structure variation | Allowed | |
| Color variation | Allowed | |
| Worm hole | Not allowed | |
| Blue stained | Not allowed | |
| Stain (discoloration) | Not allowed | |
| Rot | Not allowed | |


PRODUCT DESCRIPTION

Moland engineered wood flooring



Date: Jan. 2021

Packing



Pallets

| Number of boards per pack | 8 | boards |
|---------------------------|--------|--------|
| M² / pack | 3,58 | m² |
| Packs / pallet | 40 | packs |
| Layer / pallet | 10 | layers |
| M² / pallet | 143,49 | m² |